

**Dayson Polymers, LLC**  
**ABS PORENE® AP102 Property Data Sheet**  
**Acrylonitrile Butadiene Styrene**  
**Plating Grade**

Property	Test Condition	Nominal Values (English)	Test Method
<b>Physical</b>			
Melt Flow Rate	220°C/10.0 kg – G	18 g/10 min	ASTM D1238
<b>Mechanical</b>			
Tensile Strength	73°F	6,190 psi	ASTM D638
Flexural Modulus	73°F	334,249 psi	ASTM D790
Flexural Strength	73°F	8,820 psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact	73°F, 0.250 in	4.59 ft.lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness	R-Scale, 0.250 in	112	ASTM D785
<b>Thermal</b>			
DTUL @ 264 psi - Unannealed	0.250 in	190 °F	ASTM D648
DTUL @ 66 psi - Unannealed	0.250 in	205 °F	ASTM D648
<b>Ignition Characteristics</b>			
Flame Rating – UL (0.126in)		HB	UL-94
<b>PROCESSING INFORMATION</b>			
<b>Injection Molding Parameters</b>		<b>Nominal Values (English)</b>	
Drying Temperature		176 to 185 °F	
Drying Time		2.0 to 3.0 hr	
Processing (Melt) Temp		356 to 482 °F	
Mold Temperature		104 to 140 °F	

**APPLICATION: INJECTION MOLDING**

**ELECTRICAL PARTS, AUTOMOTIVE APPLICATIONS, HOUSEHOLD GOODS, TOYS**

**PORENE® IS A REGISTERED TRADEMARK OF THAI ABS COMPANY LIMITED**

Remark: The values presented on the above are typical laboratory averages. All data generated is based on natural material.

To the best of our knowledge the information contained in this publication is accurate, however, we do not assume any liability whatsoever for the accuracy or completeness of such information. Since we have no control over the use to which others may put our product, we cannot guarantee that results will be the same as those described in this publication will be obtained. The buyer assumes sole responsibility for results obtained in reliance upon this publication. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves as to such suitability and they can meet all applicable safety and health standards.