

Dayson Polymers, LLC
TRIBIT® 1500 High Flow
Polybutylene Terephthalate

Property	Test Condition	Nominal Values (English)	Test Method
Physical			
Density – Specific Gravity	sp gr 23/23°C	1.31	ASTM 792
Melt Flow Rate	250°C/5.0kg	220 g/10min	ASTM D1238
Mold Shrink, Linear-Flow	in/in	0.015 to 0.023	ASTM 955
Water Absorption @ 24 hours	%	.10	ASTM D570
Mechanical			
Tensile Strength @ Yld		7,960 psi	ASTM D638
Tensile Elongation @ Yld	%	4.0	ASTM D638
Tensile Elongation @ Break	%	40	ASTM D638
Flexural Modulus		341,040 psi	ASTM D790
Flexural Strength @ Yld		11,800 psi	ASTM D790
Impact			
Notched Izod Impact (0.500in)	ft-lb/in	0.64	ASTM D256
Notched Izod Impact (0.125in)	ft-lb/in	1.47	
Hardness			
Rockwell Hardness	R-Scale	118	ASTM D785
Thermal			
DTUL @ 264 psi - Unannealed		140 °F	ASTM D648
DTUL @ 66 psi - Unannealed		311 °F	
Melting Point		428 to 437 °F	
CLTE, Flow	in/in/°F	5.0E-005	ASTM D696
Specific Heat	Btu/lb/°F	0.500	ASTM C351
Electrical			
Volume Resistivity		1.0E+016 ohm-cm	ASTM D257
Dielectric Strength	V/mil	432	ASTM D149
Dielectric Constant	1000000 Hz	3.200	ASTM D150
Dissipation Factor	1000000 Hz	0.0200	ASTM D150
Arc Resistance	sec	180	ASTM D495
Ignition Characteristics			
Flame Rating – UL		HB	UL94

PROCESSING INFORMATION

INJECTION MOLDING PARAMETERS	NOMINAL VALUES (ENGLISH)
DRYING TEMPERATURE	248 °F
DRYING TIME	5.0 HR
REAR TEMPERATURE	455 °F
MIDDLE TEMPERATURE	473 °F
FRONT TEMPERATURE	473 °F
NOZZLE TEMPERATURE	473 °F
PROCESSING (MELT) TEMP	482 to 509 °F
MOLD TEMPERATURE	104 to 176 °F
INJECTION PRESSURE	4260 to 5680 psi
SCREW SPEED	80 rpm

TRIBIT® is a registered trademark of Sam Yang Engineering Plastics.

Remark: The values presented on the above are typical laboratory averages. All data generated is based on natural material. To the best of our knowledge the information contained in this publication is accurate, however, we do not assume any liability whatsoever for the accuracy or completeness of such information. Since we have no control over the use to which others may put our product, we cannot guarantee that results the same as those described in this publication will be obtained. The buyer assumes sole responsibility for results obtained in reliance upon this publication. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves as to such suitability and they can meet all applicable safety and health standards.