

Dayson Polymers, LLC

TRIEX® POLYCARBONATE 3025N1 Flame Retardant

Property	Test Condition	Nominal Values (English)	Test Method
Physical			
Density – Specific Gravity	sp gr 23/23°C	1.24	ASTM 792
Mold Shrink, Linear-Flow (0.118in)	in/in	0.0050 to 0.0070	ASTM 955
Water Absorption @ 24 hours	%	.14	ASTM D570
Mechanical			
Tensile Strength		9,670 psi	ASTM D638
Tensile Elongation @ Break	%	100	ASTM D638
Flexural Modulus		327,137 psi	ASTM D790
Flexural Strength		12,700 psi	ASTM D790
Impact			
Notched Izod Impact (0.125in)	ft-lb/in	13.78	ASTM D256
Hardness			
Rockwell Hardness	R-Scale	122	ASTM D785
Thermal			
DTUL @ 264 psi - Unannealed		271 °F	ASTM D648
DTUL @ 66 psi - Unannealed		291 °F	ASTM D648
CLTE, Flow	in/in/°F	3.1E-005	ASTM D696
Electrical			
Volume Resistivity		4.0E+016 ohm-cm	ASTM D257
Dielectric Strength	V/mil	762	ASTM D149
Dielectric Constant	1000000 Hz	2.800	ASTM D150
Dissipation Factor	1000000 Hz	0.0082	ASTM D150
Arc Resistance	sec	90.0	
Ignition Characteristics			
Flame Rating – UL (0.0625in)		V-0	UL94
Flame Rating – UL (0.125in)		V-0	UL94
Optical			
Transmittance	%	88.0	ASTM D1003

PROCESSING INFORMATION

INJECTION MOLDING PARAMETERS	NOMINAL VALUES (ENGLISH)
DRYING TEMPERATURE	248 °F
DRYING TIME	6.0 HR
REAR TEMPERATURE	464 to 536 °F
MIDDLE TEMPERATURE	518 to 590 °F
FRONT TEMPERATURE	518 to 590 °F
NOZZLE TEMPERATURE	518 to 572 °F
PROCESSING (MELT) TEMP	518 to 590 °F
MOLD TEMPERATURE	158 to 230 °F
INJECTION PRESSURE	11400 to 19900 psi

AUTOMOTIVE APPLICATIONS, ELECTRICAL/ELECTRONIC APPLICATIONS, PACKAGING, FOOD

***HF: High Flow, IR: Ice Clear and Releasing Agent, U: UV-Stabilized,**

***-02: Blue Tinted Grade**

TRIEX® is a registered trademark of Sam Yang Engineering Plastics.

Remark: The values presented on the above are typical laboratory averages. All data generated is based on natural material.

To the best of our knowledge the information contained in this publication is accurate, however, we do not assume any liability whatsoever for the accuracy or completeness of such information. Since we have no control over the use to which others may put our product, we cannot guarantee that results will be the same as those described in this publication will be obtained. The buyer assumes sole responsibility for results obtained in reliance upon this publication. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves as to such suitability and they can meet all applicable safety and health standards.